

EN 60332-1-2

Clause	Requirement + Test	Result - Remark	Verdict
ZTT 2.0mm (ZTT 0972)			
5	Procedure		
	Sample length (600 ± 25 mm).....	615	P
	Approx. outer diameter (mm).....	2,0	
	Flame application time (s).....	60	P
6	Evaluation of test results		
	Not damaged area from lower edge of the top support (min. 50 mm).....	387	P
	Damaged area from lower edge of the top support (max. 540 mm).....	490	P
	Flame spread H (max. 425 mm).....	103	P




Photo documentation
Before test
After test

13

Measuring equipment list

Device	Manufacturer	Type	Identification No.	Next calibration
Measuring tape	Stabila	BM 30W	503509	2019.09.21.
Stop-watch	Helvetia	S001	502911	2017.10.25.
Digital caliper	Mitutoyo	CD-15B	0556014003	2018.01.03.
Digital temperature and humidity meter	Testo	testo 635	023302	2018.01.24.
1 kW pre-mixed burner	MEEI	-	01629026	2018.03.14

-END OF TEST REPORT-