

Clause	Requirement + Test	Result - Remark	Verdict
--------	--------------------	-----------------	---------

ZTT 3.0mm (ZTT 0978)

5 Procedure

Sample length (600 ± 25 mm).....	615		P
Approx. outer diameter (mm).....	3,0		
Flame application time (s)....	60		P

6 Evaluation of test results

Not damaged area from lower edge of the top support (min. 50 mm).....	393		P
Damaged area from lower edge of the top support	400		P

(max. 540 mm).....

Photo documentation

Before test
After test
Measurement list

Device	Manufacturer	Type	Identification No.	Next calibration
Measuring tape	Stabila	BM 30W	503509	2019.09.21.
Stop-watch	Helvetia	S001	502911	2017.10.25.
Digital caliper	Mitutoyo	CD-15B	0556014003	2018.01.03.
Digital temperature and humidity meter	Testo	testo 635	023302	2018.01.24.
1 kW pre-mixed burner	MEEI	-	01629026	2018.03.14

-END OF TEST REPORT-